

Danish Indoor Climate Labelling



Testing and labelling criteria

Interior doors

3rd edition, January 2018

Reference to General labelling criteria	Property	Requirements
Clause 2	<i>Use(s)</i>	Interior doors and portable walls as delivered from the supplier. The criteria cover all components which may be part of interior doors and portable walls such as door leaves, door frames and joints. Products may be surface treated.
Clause 5.2	<i>Materials needed for completion</i>	Some products may need treatment before use or in the initial phase of the product's life span. If treatment of the product or other supplementary products are necessary or recommended by the manufacturer, it should be stated whether these products or treatments are included in the test.
Clause 6.5	<i>Sampling</i>	Products are preferably sampled as whole units at the manufacturing site as soon as the product is ready for delivery.
Clause 7	<i>Reference room loading factor</i>	Reference room loading factor for internal doors is 0.07 m ² /m ³ (corresponding to 2 m ² in the reference room). The loading factor for portable walls is 0.13 m ² /m ³ (corresponding to 4 m ² in the reference room)
Clause 7.1	<i>Test specimen preparation</i>	Interior doors are tested with factory finished edges unsealed. Portable walls are tested including mechanically fastened joints. The length of the joint per area unit shall reflect the average in real use.
Clause 8.2	<i>Maximum allowed time-value</i>	Interior doors: 80 days Portable walls: 100 days