

# Danish Indoor Climate Labelling



## Testing and labelling criteria Textile floor coverings 4<sup>th</sup> edition, January 2018

Reference to General labelling criteria	Property	Requirements
Clause 2	<i>Use(s)</i>	Textile floor coverings with integrated back. The carpets are grouped according to the backing material (e.g. latex, textile etc.).
Clause 5.2	<i>Materials needed for completion</i>	<p>It should appear, whether the supplier prescribes the use of other materials for installation, and whether these materials are included in the labelling license.</p> <p>Some products may need treatment before use or in the initial phase of the product's life span. If treatment of the product or other supplementary products are necessary or recommended by the manufacturer, it should be stated whether these products or treatments are included in the test.</p>
Clause 6.5	<i>Sampling</i>	<p>Unopened retail packages are sampled for testing whenever appropriate.</p> <p>Sampling from large and heavy product rolls: Discard at least two outer layers of the roll. Cut at least 1 m sample of full roll width. Roll the sample tightly and wrap in inert and airtight wrapping.</p>
Clause 7	<i>Reference room loading factor</i>	Loading factor corresponds to floor area and appear from EN 16516.
Clause 7.1	<i>Test specimen preparation</i>	Test specimen is taken symmetrically from the middle of the material sample excluding minimum 10 cm from factory finished edges. Backside and edges of the product is covered.
Clause 8.2	<i>Maximum allowed time-value</i>	60 days